DreamTec+ Underlay click vinyl planks



63000027
Size underlay H 1180 x L8500 x TH 1,5 mm
Per box (2,2787 kg net)
27 boxes / pallet = 270 m² (61,52 kg net)
Pressure resistant foam non woven with antislip surface and integrated water vapour layour.
Exceptional compressive strength and dynamic load resistance, which ensures extended durability With integrated water vapour layer to avoid moisture diffusion Outstanding damping of walking sound and good damping of impact sound low thermal resistance: applicable for floor heating systems.
Easy installation: folds out flat straight away , for floating installation Sliceable with a standard cutter knife.

BERRY ALLOC°

Requirements

Characteristics	Method	Value	Unit
Thickness of the underlay measured	EN 823	1,5 (<u>+</u> 15%)	mm
Foam colour		Silver	
Reflected walking sound	ISO 10140	<u><</u> 3	dB (A)
Impact sound reduction	ISO 10140	20	dB
Compressive strength	EN 826	CS > 400	kPa (-40 t∕m²)
(at 0,5 mm deformation)			
Punctual conformability to even out uneveness of subfloor	ISO 868/ TS 16354	+- 1	mm
Thermal Resistance	DIN 4108	0,043	m² K∕W
Water absorption	EN 12087	< 1	%
Coefficient of friction	ISO 8295	> 0,8	
Dynamic load resistance	EN 13793/ TS 16354	DL > 100.000	cycles
Deflection temp. under load		< 70	°C

Storage conditions:

Do not store outdoors, protect from exposure to sunlight.Prevent electrostatic discharges, keep away from ignition source, do not smoke

Chemical resistance:

Against water, most domestic cleaners, solutions of salt.





The above figures are based on the current state of knowledge and technical development level's, and can not be subject of claims about completeness. Technological changes and advancements reserved.