


EMOTIONS



Emissions tested in accordance with DIBt-principles



Product Information

| | | | |
|----------------------|------------------------|--|------------------------|
| Usage classification | EN ISO 10874 EN 685 | | 23 - 31 |
| Wear layer | EN ISO 24340 EN 429 | | 0,25 mm |
| Total thickness | EN ISO 24346 EN 428 | | 2,50 mm |
| Total weight | EN ISO 23997 EN 430 | | 1650 gr/m ² |
| Standart widths | EN ISO 24341 EN 426 | | 4m |
| Standard length | EN ISO 24341 EN 426 | | 30m |

Technical Information

| | | | |
|-----------------------|--------------------------|--|-----------|
| Light stability | EN ISO 105 B02 | | ≥ 6 |
| Dimensional Stability | EN ISO 23999 EN 434 | | ≤ 0,40 % |
| Underfloor heating | EN 12667 | | Suitable |
| Residual Indentation | EN ISO 24343-2 EN 433 | | ≤ 0,35 mm |
| Reaction to fire | EN 13501-1 | | Bfl/S1 |
| Slip resistance | DIN 51130 | | R10 |