

NEW PLAN

FLOOR & WALL
MATERIALS

VERDI

S. No.	CHARACTERISTIC	TEST METHOD	RESULT
1	THICKNESS (mm)	EN-428	1.00
2	TOTAL WEIGHT (gm/sqm)	EN-430	1.80 KG
3	DIMENSION	EN-426	2Mtr x 30Mtr =60Sq Mtr
4	RESIDUAL INDENTATION (mm)	EN-443	<0.10 MM
5	ABRASION RESISTANCE	EN 660-2/EN 469	WEAR GROUP M
6	DIMENSIONAL STABILITY (%)	EN-434	<0.40o/o
7	RESISTANCE TO CHEMICALS	EN 423	NO VISIBLE CHANGE
8	FIRE PROPAGATION	BS 476 PART 6	(I)=10.8) CLASS "O" (II)=1.7
9	SURFACE SPREAD OF FLAME	BS 476 PART 7	CLASS 1
10	COLOR FASTNESS TO DAYLIGHT	IS : 9766	>5
11	TENSILE STRENGTH (Kg/Cm 2)	IS:3464	65 (MIN.)
12	TEAR STRENGTH (Kg/Cm)	IS: 2076	10 (MIN.)
13	HARDNESS (SHORE A)	ASTMD 2240	80-85
14	SLIP RESISTANCE	DIN 51130	R10
15	SOUND ABSORPTION	ISO 140-8 EN ISO 717-2	▽ LW= 4 DB
16	PERFORMANCE CLASSIFICATION	EN 685	31, 32
17	FLEXIBILITY	EN 435	40MM MANDREL, PASSED